




SPRAY GUN SET UP SELECTOR: Gun Inlet Pressure 2.0 bar or as stated




PRI Filler/Primer Gun




GTi Pro Topcoat Gun




GTi Pro Topcoat Gun



GTi Pro Topcoat Gun



SRI Pro Spot Repair Gun



SRI Pro Spot Repair Gun

Air Cap No & Technology:

		P1 (Trans-Tech)	H1 (HVLP)	T1 (Trans-Tech)	T2 (Trans-Tech)	HS1 (HVLP)	TS1 (Trans-Tech)
Wash Primer	1-15	1.6 - 1.8 mm	Use GTi Pro T2	Use GTi Pro T2	1.3 - 1.4 mm	Use SRI Gun	0.8 - 1.0 mm
Epoxy Primer	1-70 white and beige	1.6 - 1.8 mm	Use PRI	Use PRI	Use PRI	Use SRI Gun	1.0 - 1.2 mm
Epoxy Primer Wet on Wet	1-70 white and beige	Use GTi Pro T2	Use GTi Pro T2	Use GTi Pro T2	1.3 - 1.4 mm	Use SRI Gun	1.0 - 1.2 mm
HS Surfacer 2K	8-145 2K HS grey 8-145/10 2K HS white 8-145/40 2K HS black	1.6 - 1.8 mm	Use PRI	Use PRI	Use PRI	Use SRI Gun	1.0 - 1.2 mm
HS Surfacer 2K Wet on Wet	8-145 2K HS grey 8-145/10 2K HS white 8-145/40 2K HS black	Use GTi Pro T2	Use GTi Pro T2	Use GTi Pro T2	1.3 - 1.4 mm	Use SRI Gun	1.0 - 1.2 mm
Waterbase Topcoat	Series 900	Use GTi Pro T1	1.3 mm	1.3 mm	Use GTi Pro T1	1.0 - 1.2 mm	1.0 - 1.2 mm
Clearcoat	8-104 2K HS	Use GTi Pro T2	Use GTi Pro T2	Use GTi Pro T2	1.3 - 1.4 mm	Use SRI Gun	1.0 - 1.2 mm
	8-204 HS 420gr/ltr	Use GTi Pro T2	Use GTi Pro T2	Use GTi Pro T2	1.3 - 1.4 mm	Use SRI Gun	0.8 - 1.0 mm
Solid Colour 2K LD	Series 3000 2K HS 420 gr/ltr	Use GTi Pro T2	Use GTi Pro T2	Use GTi Pro T2	1.3 mm	Use SRI Gun	1.0 - 1.2 mm